

# TECHNICAL DATASHEET

10130DSC12X06X / #12247



# GORI 06 UNIVERSAL Wood Oil

GORI 06 Universal is a natural, colourless, water repellent teak oil. It enhances the wood grain and enables wood to recover its natural balance.

## PRODUCT DESCRIPTION

<b>Where to use</b>	Garden furniture, in particular exotic and tropical woods, and noble indoor wood.
<b>Form supplied</b>	Ready to use.
<b>Substrate</b>	The surface must be clean, dry, and solid.
<b>Pre-treatment</b>	Before treatment: clean surface with white spirit or PPG Power Cleaner. Remove stains using sandpaper soaked in GORI 06.
<b>Treatment</b>	Apply using a soft cloth or paint brush. Wipe with a clean cloth after app. 10 min.
<b>Application method</b>	Brush or cloth. Avoid application in direct sunlight. During application and drying, the temperature must be above 5°C and relative humidity below 50%.
<b>Thinning</b>	Do not thin.
<b>Cleaning of tools</b>	White spirit.

## TECHNICAL PRODUCT DESCRIPTION

<b>Odour</b>	Strong. Odourless after drying.
--------------	---------------------------------



PRODUCT EMG: 10130DSC12X06X  
DATE OF ISSUE: 2024-11-27  
PAGE: 1



# TECHNICAL DATASHEET

10130DSC12X06X / #12247



<b>Coverage</b>	App. 7-12 m <sup>2</sup> /l. Coverage varies according to type of wood, wood porosity, surface condition, wood species, cut structure and direction.
<b>Drying time</b>	<u>Touch dry</u> : app. 6-12 hours. <u>Recoatable</u> : app. 24 hours. Measured at 23°C and humidity below 50%.  Deviations may occur depending on temperature, humidity, ventilation, and layer thickness. Terrace can be used 2 days after application.
<b>Shelf life</b>	5 years in unopened container. Limited shelf life after opening.
<b>Storage</b>	Store and transport frost free in tightly closed container. Store in a dry and cool area away from direct sunlight.

## TECHNICAL DATA

<b>Product type</b>	Natural oil.
<b>Density</b>	0.87-0.90 g/m <sup>3</sup> .
<b>Flash point</b>	63°C.
<b>Solid content</b>	41.4-46.3 vol. %.
<b>Viscosity</b>	Thin.
<b>Gloss</b>	Matt.

## COMPOSITION

<b>Binder</b>	Alkyd/linseed oil.
<b>Solvent</b>	Aliphatic hydrocarbons/white spirit.
<b>Pigments</b>	Organic and inorganic pigments.
<b>Additives</b>	None.

## SAFETY AND ENVIRONMENT

<b>General</b>	Common safety rules for work with paints and varnishes must be observed. Further information is available from our safety data sheet on <a href="http://www.gori.com">www.gori.com</a> .
----------------	--

# TECHNICAL DATASHEET

10130DSC12X06X / #12247



## Disposal

Do not empty into drains or into the environment. Do not pour product waste into sewers, water reserves or soil. Hand in left over product at your local waste disposal. Empty can be recycled (check with your local waste disposal site or your local authorities).

## ADDITIONAL INFORMATION

### Wood species

Western Red Cedar, Alaska Yellow Cedar, Larch, and similar types of wood contain tannin, which may repel coating and/or staining. Please make a test on a small area before treating and check the final result.

Please also note that all softwood may retract or swell up to 12 %. No film can adapt to this kind of movement and therefore a maximum of 18 % humidity is the limit for applying treatment.

Iroko, Teak, Rubber wood and some other wood species contain "oil", which may delay drying and thereby give an uneven surface after application. You can try cleaning the surface with cellulose thinner and then sand with grit 220. Then apply GORI 06 on a small test area. We stress that there is no guarantee for a satisfactory result.

Ipe turns grey after coating with wood oils, but by power-washing after coating is worn down you may return to original colour.

As wood is an organic material, there is no guarantee that the same wood species will react the same way in different areas, when treated/coated/stained. For more information and safety data sheets: [www.gori.com](http://www.gori.com).

---

*The purpose of this Technical Data Sheet is to provide our clients with information about the properties and characteristics of the product. The information provided, is based on tests conducted by us under usage conditions that comply with the prevailing standards. Our recommendations for use are for information only, and in no event shall they take precedence over any specific recommendation taking into account the nature and conditions of a particular site, nor shall they engage PPG's liability. Before all applications of the product, clients should check that this document has not been amended by a more recent version, which takes into account new technical data. This version annuls and replaces all previous versions of Technical Data Sheets relating to this product. Download Technical Data Sheets [www.gori.com](http://www.gori.com).*

---

PPG Coatings Danmark A/S  
Gladsaxevej 300  
DK-2860 Søborg  
Tel: +45 39 57 93 00  
[export@ppg.com](mailto:export@ppg.com)  
[www.gori.com](http://www.gori.com)



PRODUCT EMG: 10130DSC12X06X  
DATE OF ISSUE: 2024-11-27  
PAGE: 3

**GORI**<sup>®</sup>  
Professional